

Auscon FS 35 Tilers Screed is designed to be used over concrete, fibre cement floors before laying waterproofing, tiles, and pavers. It is a pre-mixed blend that is 1 part cement and 3 part sand, ideal for achieving falls for water run-off, or levelling uneven concrete floors. Suitable for internal and external use.

Application, Advantages and Solution

- Concrete repairs
- Floor and wall repairs
- Used internally and externally
- Used under natural stone and ceramic tiles
- High build
- High strength
- Pre-mix - just add water
- Used over concrete floors

Mixing Instructions

1. Place 80% of the water into the mixing vessel
2. Slowly add 70% of the powder to the mixing vessel, and mix for 1 minute
3. Add the final 20 % of the water to the mixing vessel
4. Slowly add the remainder of the powder to the mixing vessel
5. Mix for 3 minutes or until uniform

Water Ratio Limits	Litres per 20 kg bag
Dry pack	2.0 – 2.2

Applying Mixed Material

- Application thickness: 5mm to 40 mm
- Do not exceed the recommended thickness in any layer
- Do not mix more material than can be placed in 15 minutes
- Apply small amounts of mixed material into the surface and trowel to a smooth finish

IMPORTANT: Do not mix cementitious products if the temperature is expected to exceed 30 °Celsius, or if the change in ambient temperature exceeds +/- 12 °Celsius

Surface Preparation

- All defective host substrate must be removed before application
- Defective material includes cracked or structurally weakened surfaces
- Host concrete must be roughened and aggregate exposed to ensure a good bond
- For chloride contaminated concrete, a concrete corrosion expert must be consulted
- All concrete substrates **MUST** be first primed with BP 007 primer before applying Auscon FS 35

All surfaces must be free from dust, oils, and surface contaminants. This may require cleaning with high-pressure water blasting or saturation to the surface using water before applying materials



For More Information contact Auscon Australia

Test Characteristic

Property	Test Method	Results
Cement	AS 3972	Complies
Aggregate / Sand	AS 2758	Complies
Compressive Strength	AS 1478.2 (Appendix A)	Complies
Initial Set (Approximate)	AS 1012.18	180 minutes @ 20 °C
Final Set (Approximate)	AS 1012.18	300 minutes @ 20 °C
Maximum Particle Size	1.8 mm	
Mixing Time	3 Minutes	

Compressive Strength

Minimum MPa	MPa @ 24hrs	MPa @ 7 days	MPa @ 28 days	Water / 20kg
Dry Pack	10	20	30	2.0

The Data testing was conducted in a controlled laboratory environment field results may vary and is beyond Auscon Australia control

- **Storage** - Store undercover in cool, dry conditions
- **Shelf Life** - 12 Months if unopened and kept in a dry location. Best to use within 6 months from purchase date
- **Clean up** - Clean tools and surfaces using clean water within 30 minutes of applying materials or prior to curing
- **Packaging** - 20kg paper bag, 48 bags per pallet, pallet weight 990kg, (including pallet)
- **Disposal** - Keep out of sewer and stormwater lines. In the interest of the environment, please dispose of empty bag and materials as trade waste in accordance with local authority guidelines.
- **Safety Information** - The end-user of this product must first read the latest version of the Safety Data Sheets at www.auscon.net.au before this product can be used.

Auscon products are manufactured using ISO 9001 Certified Processes.

Version – June 2020

DISCLAIMER - The end use of this product is beyond the manufacturer's control and liability is restricted to the replacement of material proven to be faulty. The manufacturer is NOT responsible for any loss or damage arising from incorrect usage of this product. The information contained herein is provided in good faith and to best of Auscon Australia knowledge is true and accurate. No warranty is implied or given as to its completeness or accuracy in describing the performance or suitability of the product for an application.

Users are requested to check that the literature in their possession is of the latest and correct issue, Auscon is a registered trademark of Auscon Australia Pty Ltd.

The recommendations to the application and use of the Auscon Australia cement products are based on materials mixed and applied under normal conditions. Site conditions and substrates will vary.

The product must be first tested to its suitability of the intended application before use. The end user of this product must first read the latest version of the Product & Safety Data Sheets at www.auscon.net.au before this product can be used.



For More Information contact Auscon Australia